

## H-TEC™ HTMC9 Huntite / Hydromagnesite blend

### Typical Physical Properties

Mean Particle Size (microns)	0.6
Top Size -99% Less Than (microns)	15
Free Moisture (% max)	0.5
Loss on Ignition (%)	54.0
Surface Area (m <sup>2</sup> /g)	>10
Specific Gravity	2.5
Oil Absorption	40
Refractive Index	1.6
TAPPI Brightness	95+
Processing Temperature (°C)	250

### Typical Chemical Properties

MgO%	36.5
CaO%	10.5
Fe <sub>2</sub> O <sub>3</sub> %	<0.1
SiO <sub>2</sub> %	0.4

A low-cost natural mineral, a consistent mixture of huntite, a magnesium calcium carbonate [Mg<sub>3</sub>Ca(CO<sub>3</sub>)<sub>4</sub>] and hydromagnesite, a hydrated magnesium hydroxycarbonate [Mg<sub>4</sub>(CO<sub>3</sub>)<sub>3</sub>(OH)<sub>2</sub>•3H<sub>2</sub>O]. It is a bright white platy material with bimodal particle size distribution from 0.5 micron to <15 microns. HTMC9 can tolerate processing temperatures of 250°C, which is above the range for ATH.

As a successful flame retardant additive for PVC, EPDM and polyolefins, it has efficiency in the same range of magnesium hydroxide, sometimes better, but with lower cost and often processing advantages. Under fire exposure conditions, it absorbs heat and loses 54% of its weight as water and carbon dioxide to provide flame retardancy (typical loadings of 60% in polyolefins) and smoke suppression. Moreover, its platy character results in an effective fire barrier. Synergism with ATH has been reported.

Its bright white character allows use as an extender for TiO<sub>2</sub> with a good surface finish.

**APPLICATIONS:** Used in polyolefins and other polymers processed below 250°C.

**PRODUCT VARIATIONS:** This family of products is available in a variety of surface treatments to suit specific requirements. Please contact your sales representative for the HTMC9 product that is best for your application.

**HEALTH AND SAFETY:** For specific information refer to SDS

**PACKAGING:** Standard packaging is 44lb bags on 2000lb to 3000lb pallets. Some custom packaging available.

April 2019

Terms and Conditions of Sale: All statements, technical information and recommendations are based on tests we believe to be reliable, the accuracy or completeness is not guaranteed, and the following is made in place of all warranties, expressed or implied. Our only obligation is to replace product proved to be defective. We shall not be liable for any injury, loss or damage, direct or indirect, from using or not being able to use the product. Before using, customer must determine the suitability of the product for the intended use and customer assumes the responsibility. This statement may not be changed except by an agreement signed by an officer of The R.J. Marshall Company.