

MAGNAPUR® MGP-P7

PRECIPITATED MAGNESIUM HYDROXIDE

Typical Characteristics and Properties

Mg(OH) ₂	≥99%
Free Moisture	≤0.50%
Specific Gravity	2.36
Bulk Density	300-500 g/l
BET Surface Area	18 m ² /g
Particle Size	d50 1.5 μm
Sieve Residue +325 mesh	0%
Electrical Conductivity	≤350 μS/cm

Magnapur MGP-P7 is an engineered morphology precipitated uncoated magnesium hydroxide (MDH) of high purity, suitable for a wide range of halogen free thermoplastic and thermosetting polymer compounds. It is particularly suitable for wire and cable applications for jacketing and insulation compounds. In typical halogen free wire and cable compound applications, it is possible to achieve increases in Limiting Oxygen Index compared to traditional products.

MGP-P7 offers the formulator the ability to develop high quality halogen free compounds with low smoke characteristics, excellent flame retardancy and low toxicity. In addition, it exhibits high thermal stability up to 330°C and hence will work for a wide product range of polymers and process temperatures.

APPLICATIONS: Suitable for use in flexible and rigid PVC, Polyolefins, EVA, EEA, EBA, EPDM, EPR, SBR, Latexes, Urethanes, Unsaturated Polyesters, Epoxies and many other systems.

HEALTH AND SAFETY: Refer to the Safety Data Sheet

PACKAGING: Standard packaging is 25kg (55.11 lbs)

For further guidance it is recommended that customers contact matsolutions@rjmarshall.com to discuss their specific recipes.

February 2021

Terms and Conditions of Sale: All statements, technical information and recommendations are based on tests we believe to be reliable, the accuracy or completeness is not guaranteed, and the following is made in place of all warranties, expressed or implied. Our only obligation is to replace product proved to be defective. We shall not be liable for any injury, loss or damage, direct or indirect, from using or not being able to use the product. Before using, customer must determine the suitability of the product for the intended use and customer assumes the responsibility. This statement may not be changed except by an agreement signed by an officer of The R.J. Marshall Company.